

Code	0TQHST9900	FILM TECHNICAL DATA SHEET			
Type	FLUOROPOLYMER		rev.004	17/06/2020	
		Units	Technical data	Typical values	Method
<b>Dimensional Properties</b>					
Nominal thickness		µm	250	251	ISO 4593
Width		m	.	.	ISO 4592
Average thickness-tolerance vs nominal		%	+5	0,5%	ISO 4593
Minimum thickness measured		%	-10	-2,4%	
<b>Mechanical Properties</b>					
Tensile strength at break MD		MPa	>40	49	EN ISO 527-3
Tensile strength at break TD		MPa	>40	49	
Tensile strain at break MD		%	>300	380	
Tensile strain at break TD		%	>300	370	
Yield stress (10%)		Mpa	>20	22	
Tensile Modulus		Mpa	>950	955	
Trouser tear method TD		N/mm	>400	474	DIN 53363
Creep test MD		%	0,5	.	8.5 EN 13206
Dart test		cN	.	.	Int.Method (IO 82.4002)
<b>Optical Properties</b>					
Visible transmittance (380:780 nm)			>88	90,4%	EN 2155-5
Solar heat gain factor (300:2500 nm)		%	.	.	EN 2155-9
Colour opacity			.	.	X-RITE
<b>Other Properties</b>					
Surface Tension		dyne/cm	.	.	Geometric
Surface weight (theoretical)		g/m <sup>2</sup>	438	.	Int.Method DIN 4102 B1
Fire classification					ASTM E108 A

I valori tipici riportati sono suscettibili di variazione - Typical values reported may vary

YOUR CHOICE FOR FLUOROBASED PRODUCTS  
**GUARNIFLON®**

**GUARNIFLON SPA**  
(Società Socio Unica Soggetta all'attività di direzione e coordinamento  
ex art.2497 bis C.C. da parte di Mazza Holding srl)

VIA T.TASSO N° 12 - 24060 CASTELLI CALEPIO (BG) ITALY  
VAT N° IT 01406020162 - C.F. 01406020162  
REG.IMPRESSE DI BG - REA N. 203233  
CAPITALE SOCIALE € 10.000.000 interamente versato

**PATI DIVISION**  
Via Beltrami, 50/52 31020  
San Zenone degli Ezzelini - Italy  
Phone: +39-0423-567326

Cast and Blow Films  
www.pati.it - info@pati.it

